



Gesteinkörnung : 0/2 Edelbrechsand UNG
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil
Werte auf die sich der produzent verpflichtet
Norme

Lieferkörnung

0 2

Norme XP P 18-545 Article 8 - EN 13043

Kategorie

a

		D/2	D	1.4D	2D							
	0.063	0.08	0.125	0.25	0.5	1	2	2.8	4	f	SE	W
Ausmas	6					20	10					
V.S.S.+U	17.0					72	98					
V.S.S.	16.0					71	96			16.00		
V.S.I.	10.0					51	86	98	100		60.00	
V.S.I.-U	9.0					50	84	97	100			

Informative Teil
Production resultat

von 24/04/23 bis 28/08/23

	0.063	0.08	0.125	0.25	0.5	1	2	2.8	4	f	SE	W
Maxi	14.2	20	31	42	48	70	96	100	100	14.22		6.3
Xk+1.25xAbstand-type	14.1	17	24	35	48	67	96	100	100	14.12		4.6
Mittelwert Xf	12.3	14	19	28	40	61	92	100	100	12.29		2.4
Xk-1.25xAbstand-type	10.5	11	13	21	33	55	89	100	100	10.47		0.3
Mini	9.1	10	13	20	29	51	87	100	100	9.06		0.6
Abstand-type	1.46	2.4	4.1	5.5	6.2	4.8	2.5	0.2	0.0	1.461		1.70

