



Gesteinkörnung : 0/2 natursand
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil

Werte auf die sich der produzent verpflichtet

Lieferkörnung

Norme

Kategorie

0 2

Norme XP P 18-545 Article 10 - EN 12620 et EN 13139

Code A

	0.063	0.125	0.25	0.5	1	D	1.4D	2D	f	FM	SE	W
Ausmas			50		40	10			10	0.6		
V.S.S.+U			75		98	97				2.55		
V.S.S.			71		95	95			10.00	2.40		
V.S.I.			21		55	85	95	100		1.80		
V.S.I.-U			17		52	83	94			1.65		

Informative Teil Production resultat

von 24/04/23 bis 28/08/23

	0.063	0.125	0.25	0.5	1	2	2.8	4	f	FM	SE	W
Maxi	1.1	7	44	85	92	95	99	100	1.12	2.39		9.3
Xk+1.25xAbstand-type	1.1	6	42	81	87	93	99	100	1.05	2.42		7.2
Mittelwert Xf	0.7	3	35	73	80	90	97	100	0.72	2.18		4.0
Xk-1.25xAbstand-type	0.4	1	29	65	74	86	96	100	0.39	1.95		0.8
Mini	0.2	1	27	64	74	85	95	100	0.16	1.82		0.1
Abstand-type	0.27	1.7	5.1	6.6	5.1	2.7	1.1	0.0	0.265	0.190		2.60

