



Gesteinkörnung : 0/4 R Mischung
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil

Werte auf die sich der produzent verpflichtet
Norme

Lieferkörnung

0 4

Norme XP P 18-545 Article 10 - EN 12620 et EN 13139

Kategorie

A

	0.063	0.125	0.25	0.5	1	2	D	1.4D	2D	f	FM	SE	W
Ausmas	6		40		40		10			6	0.6		
V.S.S.+U	9.0		60		91		100			9.00	2.91		
V.S.S.	8.0		56		88		99			8.00	2.76		
V.S.I.	2.0		16		48		89	95	100	2.00	2.16	65.00	
V.S.I.-U	1.0		12		45		87	94		1.00	2.01	59.00	

Informative Teil Production resultat

von 24/04/23 bis 28/08/23

	0.063	0.125	0.25	0.5	1	2	4	5.6	8	f	FM	SE	W
Maxi	5.2	11	41	69	76	85	97	100	100	5.17	2.74		9.0
Xk+1.25xAbstand-type	4.9	10	40	66	73	84	96	100	100	4.90	2.62		6.8
Mittelwert Xf	4.0	9	35	62	70	82	96	99	100	3.95	2.47		3.8
Xk-1.25xAbstand-type	3.0	7	31	57	66	79	95	99	100	3.01	2.33		0.8
Mini	2.0	6	28	53	64	79	94	99	100	2.03	2.29		0.0
Abstand-type	0.75	1.4	3.4	3.6	2.8	1.7	0.6	0.2	0.0	0.752	0.110		2.40

