



Gesteinkörnung : 2/5.6 edelsplitt
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil

Werte auf die sich der producent verpflichtet

Lieferkörnung

Norme

Kategorie

2 5.6

Norme XP P 18-545 Article 8 - EN 13043

Fab I

		d/2	d	D/1.4		D		1.4D	2D				
	0.063	1	2	4	5	5.6	6.3	8	11.2	Cg	f	FI	W
Ausmas			10	30		10							
V.S.S.+U		6	15	86		100		100			0.80	24.00	
V.S.S.	0.5	5	10	80		99		100			0.50	20.00	
V.S.I.		0	0	25		90		98	100				
V.S.I.-U		0	0	19		85		97					

Informative Teil Production resultat

von 15/05/23 bis 28/08/23

	0.063	1	2	4	5	5.6	6.3	8	11.2	Cg	f	FI	W
Maxi	0.1	0	6	71	93	97	100	100	100	C95/1	0.10	17.13	8.1
Xk+1.25xAbstand-type	0.1	0	5	69	92	97	99	100	100		0.08		8.6
Mittelwert Xf	0.1	0	4	65	89	96	99	100	100	C95/1	0.06	12.22	6.6
Xk-1.25xAbstand-type	0.0	0	3	62	87	95	99	100	100		0.03		4.7
Mini	0.0	0	3	61	87	94	99	100	100	C100/0	0.03	10.39	1.3
Abstand-type	0.02	0.1	1.1	3.0	1.7	0.9	0.2	0.0	0.0	0.433	0.022	2.840	1.60

