



Gesteinkörnung : 2/8 rundkies
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil

Werte auf die sich der producent verpflichtet

Lieferkörnung

Norme

Kategorie

2

8

Norme XP P 18-545 Article 10 - EN 12620 et EN 13139

EN 12620


		d/2	d	D/2			D		1.4D	2D			
	0.063	1	2	4	5	6.3	8	10	11.2	16	f	FI	W
Ausmas			20	20			15						
V.S.S.+U		6	25	25			100		100			24.00	
V.S.S.		5	20	20			99		100		1.50	20.00	
V.S.I.			0	0			85		98	100			
V.S.I.-U			0	0			80		97				

Informative Teil

Produktion resultat

von 07/06/22 bis 28/08/23

	0.063	1	2	4	5	6.3	8	10	11.2	16	f	FI	W
Maxi	0.2	1	2	16	41	74	96	100	100	100	0.23	10.54	10.7
Xk+1.25xAbstand-type	0.1	1	1	15	38	69	95	100	100	100	0.13		
Mittelwert Xf	0.1	0	0	10	28	58	91	100	100	100	0.06	9.46	4.1
Xk-1.25xAbstand-type	0.0	0	0	5	19	47	88	100	100	100	0.00		
Mini	0.0	0	0	4	17	40	87	99	100	100	0.00	7.14	1.0
Abstand-type	0.06	0.3	0.4	3.8	7.4	8.8	2.9	0.2	0.0	0.0	0.061	1.178	2.10



Dimension mm

WIL 11.04.47.53 (c) Arcade 1996,2019