



Gesteinkörnung : 4/8 concassé
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil
Werte auf die sich der produzent verpflichtet
Norme

Norme XP P 18-545 Article 8 - EN 13043

Kategorie
EN 13043

Lieferkörnung

4

8

		d/2	d		D/1.4		D		1.4D	2D			
	0.063	2	4	5	5.6	6.3	8	10	11.2	16	f	FI	W
Ausmas			10		30		10						
V.S.S.+U		6	20		86		100		100		0.80	24.00	
V.S.S.		5	15		80		99		100	100	0.50	20.00	
V.S.I.		0	0		20		90		98	100			
V.S.I.-U		0	0		14		85		97				

Informative Teil
Production resultat

von 15/05/23 bis 28/08/23

	0.063	2	4	5	5.6	6.3	8	10	11.2	16	f	FI	W
Maxi	0.1	0	11	32	49	70	98	100	100	100	0.06	15.06	8.8
Xk+1.25xAbstand-type	0.1	0	11	32	49	71	99	100	100	100	0.06		5.4
Mittelwert Xf	0.0	0	7	24	39	61	95	100	100	100	0.03	10.56	3.4
Xk-1.25xAbstand-type	0.0	0	4	16	30	51	91	100	100	100	0.00		1.4
Mini	0.0	0	3	16	27	47	90	100	100	100	0.00	7.49	1.0
Abstand-type	0.02	0.1	2.8	6.2	7.5	8.0	3.2	0.2	0.0	0.0	0.023	2.774	1.60

