



Gesteinkörnung : 0/2 Edelbrechsand UNG
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil
Werte auf die sich der produzent verpflichtet
Norme

Lieferkörnung

0	2
---	---

Norme XP P 18-545 Article 8 - EN 13043

Kategorie

a

		D/2	D	1.4D	2D							
	0.063	0.08	0.125	0.25	0.5	1	2	2.8	4	f	SE	W
Ausmas	6					20	10					
V.S.S.+U	17.0					72	98					
V.S.S.	16.0					71	96			16.00		
V.S.I.	10.0					51	86	98	100		60.00	
V.S.I.-U	9.0					50	84	97	100			

Informative Teil
Production resultat

von 14/04/25 bis 28/07/25

	0.063	0.08	0.125	0.25	0.5	1	2	2.8	4	f	SE	W
Maxi	15.7	19	25	37	54	71	96	100	100	15.71		4.8
Xk+1.25xAbstand-type	14.6	17	22	35	53	73	97	100	100	14.57		3.7
Mittelwert Xf	12.3	14	18	28	43	64	94	100	100	12.33	70.68	2.4
Xk-1.25xAbstand-type	10.1	11	14	22	34	55	91	100	100	10.09		1.1
Mini	10.0	10	13	21	31	51	89	99	100	10.01		1.2
Abstand-type	1.79	2.4	3.3	5.1	7.6	7.4	2.3	0.2	0.0	1.792		1.00

