



Granulats : 16/22.4 roulé
Pétrographie : Alluvionnaire silico-calcaire

Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire

Norme

Catégorie

16 22.4

Norme XP P 18-545 Article 10 - EN 12620 et EN 13139

Code A

	d/2		D/1.4				D		1.4D		2D		f	FI	W
	0.063	8	10	12.5	14	16	18	20	22.4	25	31.5	45			
Etendue e						15			15						
V.S.S.+U	2.1	6				25			100					24.00	
V.S.S.	1.5	5				20			96				1.50	20.00	
V.S.I.		0				5			81		98	100			
V.S.I.-U		0				0			76		97				

Partie informative

Résultats de production

du 16/09/24 au 12/05/25

	0.063	8	10	12.5	14	16	18	20	22.4	25	31.5	45	f	FI	W
Maximum	0.0	0	1	4	10	20	52	76	93	99	100	100	0.05	18.65	1.5
Xf+1.25xEcart-types	0.0	0	1	4	9	21	49	74	91	99	100	100	0.03		1.5
Moyenne Xf	0.0	0	0	2	5	15	38	62	86	98	100	100	0.02	16.95	1.3
Xf-1.25xEcart-types	0.0	0	0	0	2	10	28	51	81	96	100	100	0.00		1.1
Minimum	0.0	0	0	0	1	8	26	50	81	94	100	100	0.00	14.95	1.1
Ecart-type	0.01	0.1	0.2	1.2	2.9	4.3	8.3	9.1	4.2	1.3	0.0	0.0	0.013	1.387	0.20

