



Gesteinkörnung : 2/5.6 edelsplitt
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil
Werte auf die sich der produzent verpflichtet
Norme

Lieferkörnung

2	5.6
---	-----

Norme XP P 18-545 Article 8 - EN 13043

Kategorie

Fab I

		d/2	d	D/1.4		D		1.4D	2D				
	0.063	1	2	4	5	5.6	6.3	8	11.2	Cg	f	FI	W
Ausmas			10	30		10							
V.S.S.+U		6	15	86		100		100			0.80	24.00	
V.S.S.	0.5	5	10	80		99		100			0.50	20.00	
V.S.I.		0	0	25		90		98	100				
V.S.I.-U		0	0	19		85		97					

Informative Teil
Production resultat

	0.063	1	2	4	5	5.6	6.3	8	11.2	Cg	f	FI	W
Maxi	0.2	1	6	65	88	95	99	100	100	C100/0	0.22	14.89	7.7
Xk+1.25xAbstand-type	0.2	1	5	64	88	94	99	100	100		0.15		8.0
Mittelwert Xf	0.1	0	4	58	84	93	98	100	100	C100/0	0.09	13.34	5.7
Xk-1.25xAbstand-type	0.0	0	2	52	80	91	98	100	100		0.03		3.4
Mini	0.0	0	2	47	77	91	97	100	100	C100/0	0.04	12.28	1.4
Abstand-type	0.05	0.2	1.2	4.9	3.1	1.4	0.5	0.0	0.0	0.000	0.050	1.120	1.80

