



Gesteinkörnung : 4/16R
Petrographischer Typ : Alpine Moräne - Oberheinkies und sand

Normative Teil
Werte auf die sich der produzent verpflichtet
Norme

Kategorie
Code A

Lieferkörnung

4	16
---	----

Norme XP P 18-545 Article 10 - EN 12620 et EN 13139

	0.063	d/2 2	d 4	5	5.6	6.3	D/2 8	10	12.5	D 16	20	1.4D 22.4	2D 31.5	f	FI	W
Ausmas							35									
V.S.S.+U	2.1	6	20				66			100					24.00	
V.S.S.	1.5	5	15				60			99				1.50	20.00	
V.S.I.			0				25			90		98	100			
V.S.I.-U			0				19			85		97				

Informative Teil
Production resultat

von 07/04/25 bis 28/07/25

	0.063	2	4	5	5.6	6.3	8	10	12.5	16	20	22.4	31.5	f	FI	W
Maxi	0.4	1	10	21	28	36	56	74	88	99	100	100	100	0.41	16.65	4.8
Xk+1.25xAbstand-type	0.2	0	8	19	25	34	52	68	84	99	100	100	100	0.17		4.4
Mittelwert Xf	0.0	0	5	13	19	27	43	60	77	97	100	100	100	0.04	15.29	3.4
Xk-1.25xAbstand-type	0.0	0	3	8	13	19	35	51	70	95	100	100	100	0.00		2.3
Mini	0.0	0	2	6	10	15	30	50	69	94	100	100	100	0.00	14.05	2.1
Abstand-type	0.10	0.1	2.1	4.1	4.9	5.8	6.9	6.9	5.6	1.4	0.0	0.0	0.0	0.103	1.065	0.80

