



Gesteinkörnung : 4/8 concassé
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil
Werte auf die sich der produzent verpflichtet
Norme

Lieferkörnung

4	8
---	---

Norme XP P 18-545 Article 8 - EN 13043

Kategorie

EN 13043

	d/2	d		D/1.4		D		1.4D	2D		f	FI	W
	0.063	2	4	5	5.6	6.3	8	10	11.2	16			
Ausmas			10		30		10						
V.S.S.+U		6	20		86		100		100		0.80	24.00	
V.S.S.		5	15		80		99		100	100	0.50	20.00	
V.S.I.		0	0		20		90		98	100			
V.S.I.-U		0	0		14		85		97				

Informative Teil
Production resultat

	von 07/04/25 bis 28/07/25												
	0.063	2	4	5	5.6	6.3	8	10	11.2	16	f	FI	W
Maxi	0.1	1	8	27	42	64	97	100	100	100	0.10	15.20	3.8
Xk+1.25xAbstand-type	0.1	1	8	25	40	61	96	100	100	100	0.08		3.6
Mittelwert Xf	0.1	0	6	21	35	55	93	100	100	100	0.05	12.16	3.1
Xk-1.25xAbstand-type	0.0	0	5	17	29	49	89	100	100	100	0.02		2.6
Mini	0.0	0	4	16	28	47	90	99	100	100	0.02	9.62	2.4
Abstand-type	0.02	0.1	1.3	3.3	4.2	4.8	2.8	0.3	0.0	0.0	0.024	2.307	0.40

