



Gesteinkörnung : 0/2 natursand
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil

Werte auf die sich der produzent verpflichtet

Lieferkörnung

Norme

Kategorie

0 2

Norme XP P 18-545 Article 10 - EN 12620 et EN 13139


Code A

	0.063	0.125	0.25	0.5	1	D	1.4D	2D	f	FM	SE	W
Ausmas			50		40	10			10	0.6		
V.S.S.+U			75		98	97				2.55		
V.S.S.			71		95	95			10.00	2.40		
V.S.I.			21		55	85	95	100		1.80		
V.S.I.-U			17		52	83	94			1.65		

Informative Teil Produktion resultat

von 07/07/25 bis 20/10/25

	0.063	0.125	0.25	0.5	1	2	2.8	4	f	FM	SE	W
Maxi	5.0	10	50	84	88	94	99	100	5.04	2.37		11.6
Xk+1.25xAbstand-type	2.9	9	51	84	88	94	98	100	2.86	2.27		8.8
Mittelwert Xf	1.4	6	41	77	83	91	97	100	1.43	2.02	90.50	5.1
Xk-1.25xAbstand-type	0.0	3	32	71	78	88	97	100	0.00	1.77		1.3
Mini	0.2	1	23	69	76	86	96	100	0.16	1.82		1.7
Abstand-type	1.15	2.3	7.6	5.2	4.1	2.2	0.7	0.0	1.148	0.200		3.00



Dimension mm

WIL 11.07.04.53 (c) Arcade 1996,2023