



Gesteinkörnung : 16/22.4 roulé
Petrographischer Typ : Alpine Moräne - Oberheinkies und sand

Normative Teil

Werte auf die sich der producent verpflichtet

Lieferkörnung

Norme

Kategorie

16

22.4

Norme XP P 18-545 Article 10 - EN 12620 et EN 13139

Code A


	0.063	d/2	8	10	12.5	14	d	16	18	20	D	22.4	25	31.5	45	f	FI	W
Ausmas								15				15						
V.S.S.+U	2.1	6						25				100					24.00	
V.S.S.	1.5	5						20				96				1.50	20.00	
V.S.I.		0						5				81		98	100			
V.S.I.-U		0						0				76		97				

Informative Teil

Produktion resultat

von 13/01/25 bis 27/10/25

	0.063	8	10	12.5	14	16	18	20	22.4	25	31.5	45	f	FI	W
Maxi	0.0	0	1	4	10	20	52	76	93	99	100	100	0.05	18.65	1.8
Xk+1.25xAbstand-type	0.0	0	1	4	9	20	48	73	90	99	100	100	0.04		1.7
Mittelwert Xf	0.0	0	0	2	5	14	37	61	85	97	100	100	0.02	15.80	1.3
Xk-1.25xAbstand-type	0.0	0	0	0	1	8	25	49	79	95	100	100	0.00		0.9
Mini	0.0	0	0	0	1	8	24	46	81	94	100	100	0.00	9.59	0.4
Abstand-type	0.01	0.1	0.2	1.3	3.1	4.6	9.0	9.6	4.4	1.4	0.0	0.0	0.013	2.923	0.30



Dimension mm

WIL 11.07.04.53 (c) Arcade 1996,2023