



Gesteinkörnung : 2/5.6 edelsplitt
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil
Werte auf die sich der producent verpflichtet
Norme

Lieferkörnung

2	5.6
---	-----

Norme XP P 18-545 Article 8 - EN 13043

Kategorie

Fab I

	0.063	d/2 1	d 2	D/1.4 4	5	D 5.6	6.3	1.4D 8	2D 11.2	Cg	f	FI	W
Ausmas			10	30		10							
V.S.S.+U		6	15	86		100		100			0.80	24.00	
V.S.S.	0.5	5	10	80		99		100			0.50	20.00	
V.S.I.		0	0	25		90		98	100				
V.S.I.-U		0	0	19		85		97					

Informative Teil
Production resultat

	0.063	1	2	4	5	5.6	6.3	8	11.2	Cg	f	FI	W
Maxi	0.1	1	6	68	90	96	99	100	100	C100/0	0.11	15.20	7.3
Xk+1.25xAbstand-type	0.1	0	6	68	91	96	99	100	100		0.10		7.7
Mittelwert Xf	0.1	0	4	60	85	94	98	100	100	C100/0	0.07	13.90	5.5
Xk-1.25xAbstand-type	0.0	0	2	51	80	92	98	100	100		0.05		3.2
Mini	0.0	0	0	39	72	91	97	100	100	C100/0	0.03	12.30	2.2
Abstand-type	0.02	0.1	1.4	6.5	4.5	1.6	0.6	0.0	0.0	0.000	0.021	1.205	1.80

