



Gesteinkörnung : 2/8 rundkies
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil

Werte auf die sich der produzent verpflichtet

Lieferkörnung

2	8
---	---

Norme

Norme XP P 18-545 Article 10 - EN 12620 et EN 13139

Kategorie

EN 12620

		d/2	d	D/2			D		1.4D	2D			
	0.063	1	2	4	5	6.3	8	10	11.2	16	f	FI	W
Ausmas			20	20			15						
V.S.S.+U		6	25	25			100		100			24.00	
V.S.S.		5	20	20			99		100		1.50	20.00	
V.S.I.			0	0			85		98	100			
V.S.I.-U			0	0			80		97				

Informative Teil

Produktion resultat

von 10/03/25 bis 20/10/25

	0.063	1	2	4	5	6.3	8	10	11.2	16	f	FI	W
Maxi	0.0	0	0	20	50	81	99	100	100	100	0.03	13.51	6.2
Xk+1.25xAbstand-type	0.0	0	0	21	50	81	99	100	100	100	0.02		5.9
Mittelwert Xf	0.0	0	0	15	38	70	97	100	100	100	0.01	8.44	3.9
Xk-1.25xAbstand-type	0.0	0	0	9	26	59	94	100	100	100	0.00		2.0
Mini	0.0	0	0	4	16	48	91	100	100	100	0.00	0.00	1.1
Abstand-type	0.01	0.1	0.1	4.8	9.5	8.8	1.9	0.0	0.0	0.0	0.011	3.714	1.60

