



Gesteinkörnung : 4/16R
Petrographischer Typ : Alpine Moräne - Oberheinkies und sand

Normative Teil
Werte auf die sich der produzent verpflichtet
Norme

Lieferkörnung

4 16

Norme XP P 18-545 Article 10 - EN 12620 et EN 13139

Kategorie

Code A

	0.063	d/2 2	d 4	5	5.6	6.3	D/2 8	10	12.5	D 16	20	1.4D 22.4	2D 31.5	f	FI	W
Ausmas							35									
V.S.S.+U	2.1	6	20				66			100					24.00	
V.S.S.	1.5	5	15				60			99				1.50	20.00	
V.S.I.			0				25			90		98	100			
V.S.I.-U			0				19			85		97				

Informative Teil
Produktion resultat

von 21/07/25 bis 27/10/25

	0.063	2	4	5	5.6	6.3	8	10	12.5	16	20	22.4	31.5	f	FI	W
Maxi	0.2	0	12	27	36	46	65	82	93	99	100	100	100	0.17	18.46	5.6
Xk+1.25xAbstand-type	0.1	0	11	24	33	42	61	78	91	99	100	100	100	0.08		5.2
Mittelwert Xf	0.0	0	7	16	22	29	47	63	80	97	100	100	100	0.03	15.15	4.0
Xk-1.25xAbstand-type	0.0	0	2	7	11	16	33	49	69	95	100	100	100	0.00		2.9
Mini	0.0	0	2	6	10	14	30	44	66	93	100	100	100	0.00	12.29	2.2
Abstand-type	0.04	0.1	3.5	7.1	8.8	10.2	11.2	11.5	8.6	1.5	0.0	0.0	0.0	0.044	2.540	0.90

