



Gesteinkörnung : 4/8 concassé
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil

Werte auf die sich der produzent verpflichtet

Lieferkörnung

Norme

Kategorie

4 8

Norme XP P 18-545 Article 8 - EN 13043

EN 13043

	d/2	d		D/1.4		D		1.4D	2D		f	FI	W
	0.063	2	4	5	5.6	6.3	8	10	11.2	16			
Ausmas			10		30		10						
V.S.S.+U		6	20		86		100		100		0.80	24.00	
V.S.S.		5	15		80		99		100	100	0.50	20.00	
V.S.I.		0	0		20		90		98	100			
V.S.I.-U		0	0		14		85		97				

Informative Teil Production resultat

von 28/07/25 bis 03/11/25

	0.063	2	4	5	5.6	6.3	8	10	11.2	16	f	FI	W
Maxi	0.4	1	10	29	47	70	97	100	100	100	0.37	12.88	3.2
Xk+1.25xAbstand-type	0.2	1	8	27	43	65	96	100	100	100	0.21		3.6
Mittelwert Xf	0.1	0	6	20	34	54	92	100	100	100	0.09	11.39	2.6
Xk-1.25xAbstand-type	0.0	0	3	14	24	42	89	99	100	100	0.00		1.6
Mini	0.0	0	3	12	22	41	90	99	100	100	0.02	7.58	0.4
Abstand-type	0.09	0.3	2.1	5.2	7.3	8.9	2.9	0.3	0.1	0.0	0.093	2.210	0.80

